USP 797 & 800 Compliance Specialists

Everything you need to achieve and maintain a compliant cleanroom environment

Suntech Bunny Suit:

with Zipper Front, attached hood, boots, elastic wrists

Suntech is a Microporous Film laminate material bonded to a substrate of spunbonded polypropylene providing barrier protection, comfort and strength.

Suntech is a limited use protective apparel made of the company's innovative fabric. **Suntech** is constructed of spunbonded polypropylene and laminated to Sunrise's new microporous film to provide a superior combination of strength, barrier protection, and breathability.

Designed to provide high tensile strength and flexibility, this exciting new fabric allows Sunrise to fill the gap between performance and cost in protective clothing. **Suntech** protective apparel is available in four styles of coveralls, shirts, pants, lab coats and sleeve covers. The perfect solution for a broad range of non-hazardous applications, protective garments made of **Suntech** offer superior strength, excellent wearability, a high degree of dry particulate holdout, and protection against non-hazardous liquids. Suntech also offers excellent barrier protection against blood-borne pathogens.

- · Spunbonded polypropylene reinforcedbya microporous film for hightensilestrength and flexibility.
- · Microporousfilm laminate provides superiorcombination of barrier protection and breathability.
- High degree dry particulate holdout to protect against the effects of chemical dusts, paint sprays, asbestos; and other airborne dusts.
- Designed for a broad range of non-hazardous applications including paint spray and fiberglass applications, general cleanup, pressure washing, non-hazardous liquid handling, tank cleaning, and printing.
- · Available in four styles of coveralls.

Suntech Physical Properties				
Physical Property	Test Method	Units	Test Results	
Basis Weight	ASTM D3776	oz/y²	1.85 oz/y ²	
Grab Tensile MD	ASTM D5034	lbs.	24.4 lbs.	
Grab Tensile XD	ASTM D5034	lbs.	16.2 lbs.	
Trapezoidal Tear MD	ASTM D1117	lbs.	10.8 lbs.	
Trapezoidal Tear CD	ASTM D1117	lbs.	5.4 lbs.	
Ball Burst	ASTM D3787	lbs.	25.1 lbs.	
Air Permeability	ASTM D737	cfm	<0.562 cfm/ft ²	
Surface Resistivity	EN1149-5;2006	Ω	pass	

nt spray and fiberglass nandling, tank cleaning, a	A.			
Suntech ASTM F903 Penetration Data				
Chemical Tested	Concentration %	Test Time- minutes	Test Results	
Diazinon	100%	60	Pass	
T[d¦ÁÚãÁÄÁÁÁ €Á,dÈ	100%	60	Pass	
Ó ^æ &.@#£~ @[`•^@[å	100%	60	Pass	
Q[&îæ)æc^ÁÓæe^åÁÚæájc	100%	60	Pass	
Ù[dium Hydroxide	50%	60	Pass	
Sodium Hyperchlorite	10%	60	Pass	
Blood	Challenge Fluid Liter - 3.20 x 10 ⁸	Assay Results PFU/ml<1	Pass	

(PFU/ml)

Product Numbers

CHSMP261 - S	Small	25 pcs/cs
CHSMP261 - M	Medium	25 pcs/cs
CHSMP261 - L	Large	25 pcs/cs
CHSMP261 - XL	X-Large	25 pcs/cs
CHSMP261 - 2XL	2X-Large	25 pcs/cs
CHSMP261 - 3XL	3X-Large	25 pcs/cs
CHSMP261 - 4XL	4X-Large	25 pcs/cs
CHSMP261 - 5XL	5X-Large	25 pcs/cs

